

# Roth Compact® FLEX FIX

## Description

Roth Compact® FLEX FIX is a cement-based flexible adhesive that ensures full adhesive covering and a high adhesive capacity on pressure-resistant EPS and aluminium in connection with laying of tiles on the Roth Compact® system or the Roth Clima Comfort system.

## Technical description

Water to be added:	6.0 - 6.6 L/25 kg
Mixing time:	2 - 4 minutes.
Quantity needed:	4 - 8 kg/m <sup>2</sup>
Maximum grain size:	0.5 mm
Laying thickness:	6 x 13 mm - Curved notched trowel 10 x 10 mm - Curved notched trowel
Flexural strength after 28 days:	> 18 MPa
Drying time (at +20°C, 50% RH)	6 - 8 hours
Application temperature:	+10 to +25°C.
Adhesion to primed concrete:	> 1.5 MPa
Adhesion to aluminium:	> 0.5 MPa
Workability time when opened:	60 - 90 min.
Adjustment time on tiles:	30 - 40 min.
Hardening begins:	10 - 15 min.
NS-EN 12004:2007:	C2/S1

The flow must be 155 - 165 mm (SS 923519).

## Storage

Store in a dry place. Should be used within 24 months of the production date.

UK no: 7339349818

## WARNING

30 - 60% cement

Causes skin irritation.

Causes serious eye damage.

May cause irritation of the respiratory tract.

Do not inhale the powder.

Wear protective gloves/protective clothing/eye protection/face protection.

In the event of contact with the eyes: Rinse gently with water for several minutes. Remove any contact lenses if this can be done easily.

Continue rinsing. Seek medical attention.

In the event of contact with skin: Wash with plenty of soap and water.



The product is classified as hazardous waste, but following addition of water it hardens after a few hours, and is classified as non-hazardous construction waste.  
The contents/packaging are to be disposed of using an approved waste system in accordance with any local-authority requirements.

KEEP OUT OF REACH OF CHILDREN.